

POWER BATTERY



Lithium Ion Battery Cells
for Energy Storage & EV Power

www.lishenpower.com

ORIGO Batteries

LISHEN

Weifang Lishen Power Battery System Co., Ltd.
No. 286, 2nd Street, Free Trade Zone,
Weifang City, Shandong Province
www.lishenpower.com
E-mail: info@lishenpower.com

Battery Cell & Module

LISHEN offers high-performance lithium-ion cells based around proprietary POLYMER, LFP, NMC chemistry available in cylindrical and prismatic formats. At LISHEN, all source raw materials are in accordance with international standards and practices, as well as some of LISHEN own standards to secure a supply chain free from corruption of people or planet.

High safety

- The cells have passed UL, IEC and other international certifications.
- Cell safety tested
- Lithium iron phosphate (LFP) chemistry for maximum safety and longevity

Strong environmental adaptability

- Can be discharged in -20°C~55°C environment

Good storage performance

- 25°C storage for 28 days, capacity recovery rate ≥95%;

Long warranty

100% process traceability


- Empowering each battery cell;

100% automated production

- High precision, high efficiency, to ensure the consistency of the battery cells

Data Sheet

LP54173210



MODEL NUMBER	LP54173210
Nominal Voltage	3.2V
Rated Capacity	180Ah 202Ah 230Ah
Internal Resistance(1KHz)	≤0.25mΩ
Standard charge and discharge current	0.5C/0.5C
Standard charge and discharge cut-off voltage	3.65V/2.5V
Max. charge and discharge current (Continued)	1C/1C
Max. pulse charge and discharge current(60s)	2C/2C
Recommended SOC usage range	10%-90% A.
Charge operating temperature	0°C~55°C
Discharge operating temperature	-20°C~55°C
Dimensions W/H/D (mm)	173*210*54
Weight (kg)	3.15 4.0 4.14

We reserve the right to make technical changes. The values, outputs, other technical data, images, and diagrams in this prospectus and in data sheets, advertisements, and other promotional documents are approximate guidelines in all cases where they have not been identified as binding.